



BB450 Clear Moisture Barrier Film

(High-Performance Clear Moisture Barrier Film)

Physical Properties

Available As: 2-seal pouch, 3-seal pouch, stand up pouch, sheets and tubing.

Clarity: Transparent
Thickness: 5 Mil

<u>Film Properties</u>	<u>ASTM Method</u>	<u>Typical Value</u>	<u>UNITS</u>
Tensile Strength MD	ASTM D-882	46	10 ³ psi @ break
XMD	ASTM D-882	48	10 ³ psi @ break
Tear MD	ASTM D-882	60	10 ³ psi @ break
XMD	ASTM D-882	60	10 ³ psi @ break
M.V.T.R.	Mocon	0.224	gm/100sq.in./24 hrs
Oxygen Transmission	Mocon	2.7	cc/100sq.in./24 hrs
Burst	Mullen	85	PSI